

**Description**

PRONTO (SP) 10W30 FS 6/1QT

<b>Inspection Information</b>	<b>Test Method</b>	<b>Typical Value</b>
Gravity, °API	ASTM D287	34.91
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8503
Flash Point, °C	ASTM D92	225
Flash Point, °F	ASTM D92	437
Viscosity at 40°C, cSt	ASTM D445	62.86
Viscosity at 100°C, cSt	ASTM D445	10.28
Viscosity Index	ASTM D2270	151
Pour Point, °C (°F)	ASTM D5950	-42°C (-44°F)
Cold Cranking Simulator at (°C), cP	ASTM D5293	4000 (-25)
High Temperature / High Shear Vis at 150°C, cP	ASTM D5481	3.18
Noack Volatility, % loss	ASTM D5800	5.2
Color	ASTM D1500	2.5
Zinc, wt. %	ASTM D5185	0.07
Phosphorus, wt. %	ASTM D5185	0.064
Calcium, wt. %	ASTM D5185	0.119
Sulfur, wt. %	ASTM D4951	0.161
Magnesium, wt. %	ASTM D5185	0.038
Boron, wt. %	ASTM D5185	0.007
Molybdenum, wt. %	ASTM D5185	0.004
Sulfated Ash, wt. %	ASTM D874	0.712
Nitrogen, wt. %	ASTM D4629	0.081
Pumping Viscosity at (°C), cP	ASTM D4684	21,300 (-30)
Shear Stability, Final Viscosity in cSt	ASTM D6278	9.32
Foam Seq. I (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. II (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. III (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
High Temperature Foaming, static foam	ASTM D6082 (Opt A)	20/0
TBN, mgKOH/g	ASTM D2896	7

## Claims Information

API SJ, SH, SG, SF, SE, SD, SC	Meets Requirements
API SL	Meets Requirements
API SM	Meets Requirements
API SN	Meets Requirements
API SN PLUS	Meets Requirements
API SP	Approved
Chrysler MS-6395	Meets Requirements
GM 4718M	Meets Requirements
GM 6094M	Meets Requirements
ILSAC GF-4, GF-3, GF-2, GF-1	Meets Requirements
ILSAC GF-5	Meets Requirements
ILSAC GF-6A	Approved