

**Description**

PRONTO (SP) 0W20 DXS 3/5Q

Inspection Information	Test Method	Typical Value
Gravity, °API	ASTM D287	35.66
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8465
Flash Point, °C	ASTM D92	226
Flash Point, °F	ASTM D92	439
Viscosity at 40°C, cSt	ASTM D445	44.59
Viscosity at 100°C, cSt	ASTM D445	8.475
Viscosity Index	ASTM D2270	170
Pour Point, °C (°F)	ASTM D5950	-45°C (-49°F)
Cold Cranking Simulator at (°C), cP	ASTM D5293	5800 (-30)
High Temperature / High Shear Vis at 100°C, cP	ASTM D6616	5.76
High Temperature / High Shear Vis at 150°C, cP	ASTM D5481	2.7
Noack Volatility, % loss	ASTM D5800	13
Color	ASTM D1500	3
Zinc, wt. %	ASTM D5185	0.085
Phosphorus, wt. %	ASTM D5185	0.076
Calcium, wt. %	ASTM D5185	0.135
Sulfur, wt. %	ASTM D4951	0.3
Magnesium, wt. %	ASTM D5185	0.059
Boron, wt. %	ASTM D5185	0.023
Molybdenum, wt. %	ASTM D5185	0.0079
Sulfated Ash, wt. %	ASTM D874	0.9
Nitrogen, wt. %	ASTM D4629	0.104
Pumping Viscosity at (°C), cP	ASTM D4684	21,000 (-35)
Shear Stability, Final Viscosity in cSt	ASTM D6278	7.5
Foam Seq. I (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. II (Tendency/Stability), mL	ASTM D892 (Opt. A)	5/0
Foam Seq. III (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
High Temperature Foaming, static foam	ASTM D6082 (Opt A)	20/0
TBN, mgKOH/g	ASTM D2896	7.9

## Claims Information

API SJ, SH, SG, SF, SE, SD, SC	Meets Requirements
API SL	Meets Requirements
API SM	Meets Requirements
API SN	Meets Requirements
API SN PLUS	Meets Requirements
API SP	Approved
Chrysler MS-6395	Meets Requirements
dexos1 gen 2	Approvable by Brand
Ford WSS M2C962-A1	Meets Requirements
Ford WSS-M2C947-A, WSS-M2C947-B1	Meets Requirement
GM 4718M	Meets Requirements
GM 6094M	Meets Requirements
ILSAC GF-4, GF-3, GF-2, GF-1	Meets Requirements
ILSAC GF-5	Meets Requirements
ILSAC GF-6A	Approved