

**Description**

PRONTO (SP) 80W90 5GL

<b>Inspection Information</b>	<b>Test Method</b>	<b>Typical Value</b>
Gravity, °API	ASTM D287	28.53
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8842
Flash Point, °C	ASTM D92	232
Flash Point, °F	ASTM D92	450
Viscosity at 40°C, cSt	ASTM D445	140.8
Viscosity at 100°C, cSt	ASTM D445	14.01
Viscosity Index	ASTM D2270	96
Pour Point, °C (°F)	ASTM D5950	-33°C (-27°F)
Brookfield Viscosity at -26°C, cP	ASTM D2983	100,000
Color	ASTM D1500	3
Phosphorus, wt. %	ASTM D5185	0.047
Sulfur, wt. %	ASTM D4951	1.6

## Claims Information

API GL-5	Meets Requirements
Ford M2C108C	Meets Requirements
Limited Slip	Suitable for Use
Mack GO-J, GO-H, GO-G	Meets Requirements
MAN 342 M-1	Meets Requirements
MAN 342 M-2	Meets Requirements
Meritor 0-76D	Meets Requirements
MT-1	Meets Requirements
SAE J2360, MIL-2105E/F	Meets Requirements
Scania STO 1.0	Meets Requirements
ZF TE ML-07A, ZF TE ML-08	Meets Requirements